



N.V. DOTHÉE S.A.

# RD-MULTIPRIM

## DESCRIPTION OF THE PRODUCT

|             |   |
|-------------|---|
| USE:        | Waterborne, indoor and outdoor, onecomponent universal primer. Based on acrylic polymers.   |
| FEATURES:   | Very good adhesion on most surfaces.  |
| SUBSTRATES: | Galvanized steel, glass, zinc, hard PVC, steel...   |
| SYSTEM:     | <ul style="list-style-type: none"><li>• Primer: 1 coat of RD-Multiprim;</li><li>• Topcoat: Any waterbased, acrylic coating or 1 coat of RD-Multiprim.</li></ul> |

## APPLICATION INSTRUCTIONS

|                               |   |
|-------------------------------|---|
| PREPARATION OF THE SUBSTRATE: | The substrate has to be cleaned, degreased and dry. |
| APPLICATION CONDITIONS:       | Ambient temperature: > 5° C<br>R.H.: max. 80 %      |
| APPLICATION MEANS:            | Brush or airless (nozzle: 011-015)                  |
| DILUTION:                     | Water   |
| CLEANING OF TOOLS:            | Water   |
| CONSUMPTION:                  | Ca. 10m <sup>2</sup> /L per coat                    |
| PARTICULARITIES:              | Mix well before use                                 |



**TECHNICAL DATA**

|                       |  |
|-----------------------|--|
| FINISH:               | Satin  |
| COLOURS:              | White  |
| SOLIDS CONTENT:       | In weight: ca. 54 %<br>In volume: ca. 40 %   |
| VOC CONTENT:          | Max 40g/L                                    |
| DENSITY:              | Ca. 1,3                                      |
| FLASH POINT:          | Not flammable                                |
| VISCOSITY:            | 20-30 P (Brookfield 20 Rpm)                  |
| DRYING TIME:          | On touch: 1 hour<br>Recoatable: min. 4 hours |
| PACKING:              | 1 L – 2.5 L – 5L                             |
| STORAGE<br>STABILITY: | 12 months, kept in a frost free place        |

**SAFETY DATA**

The safety data sheet is available on request.

These directions are given for information. Since the manufacturer is not able to check the right application of the products, he cannot accept any responsibility for it. This technical data sheet replaces all previous editions.