



N.V. DOTHÉE S.A.

RD-TENNISCRYL

DESCRIPTION OF THE PRODUCT

USE:	Waterborne onecomponent acrylic paint for sports grounds, especially tennis fields.
FEATURES:	Excellent flexibility - High mechanical resistance - High resistance against humidity.
SUBSTRATES:	Concrete and bitumen.
SYSTEM:	Slightly porous supports: Direct application of 2 coats on the substrate, without primer. Very porous supports: <ul style="list-style-type: none">• Primer: 1 coat of impregnation RD-UNIFIX;• Topcoat: 2 coats of RD-TENNISCRYL.

APPLICATION INSTRUCTIONS

PREPARATION OF THE SUBSTRATE:	The substrate has to be clean, dry and free of dust
APPLICATION CONDITIONS:	Outdoor: never apply if raining Ambient temperature: minimum 5° C / R.H.: max. 80 %
APPLICATION MEANS:	Brush, roller or airless (nozzle: 013-015)
DILUTION:	Water
CLEANING OF TOOLS:	Water
CONSUMPTION:	6 to 8 m ² /Kg per coat
PARTICULARITIES:	Mix before use



TECHNICAL DATA

FINISH:	Mat
COLOURS:	See colour chart
SOLIDS CONTENT:	In weight: ca. 65 % In volume: ca. 51 %
VOC CONTENT:	Max 20g/L
DENSITY:	Ca. 1.4
FLASH POINT:	Not flammable
VISCOSITY:	100 KU
DRYING TIME:	On touch: 1 hour Recoatable: 16 hours
PACKING:	5 Kg – 20 Kg
STORAGE STABILITY:	12 months: keep away from heat and frost

SAFETY DATA

The safety data sheet is available on request.

These specifications are given for information. Since the manufacturer is not able to check the right application of the products, he cannot accept any responsibility for it. This technical data sheet replaces all previous editions.